

Aspolit G400

Aspanger Aspolit is a special 3-component filler consisting of muscovite, quartz and chlorit from our own Austrian deposit. More details you can find in the separate product overview-sheet or under www.aspanger.com


General Characteristics	Specific Gravity (g/cm ³) ISO 787/10-1981	2,75
	Moh's Hardness MICA	2,5
	Moh's Hardness Quartz	7
	Whiteness FMY (%)	68
	Humidity at 100°C ISO 787/2-1981	<1
	pH ISO 787/9-1981	9,5
	Oil Absorption (g/100g) ISO 787/5-1980	12
	Spec. Surface Area (m ² /g)	1-2
Loose Bulk Density (g/l)	885	
Chemical Analysis	SiO ₂	69,0 %
	Al ₂ O ₃	15,5 %
	K ₂ O	6,5 %
	CaO	0,5 %
	Fe ₂ O ₃	2,0 %
	MgO	2,8 %
	TiO ₂	0,5 %
	P ₂ O ₅	0,2 %
Loss on ignition	3,0 %	

Aspolit G400

Particle Size
Distribution
Sieving

d98
d90
d50
d30

90,0 µm
60,0 µm
24,0 µm
15,0 µm



Technical information and data described herein are believed to be reliable, but should not be taken as a specification and cannot establish any liability!

REV 4/06-2018