

Aspolit W 58 - 500

Aspanger Aspolit is a special 3-component filler consisting of muscovite, quartz and chlorite from our own Austrian deposit. More details you can find in the separate product overview-sheet or under www.aspanger.com


General Characteristics	Specific Gravity (g/cm ³) ISO 787/10-1981	2,75
	Moh's Hardness MICA	2,5
	Moh's Hardness Quartz	7
	Whiteness FMY (%)	58
	Humidity (%) ISO 787/2-1981	<1
	pH ISO 787/9-1981	9,5
	Oil Adsorption (g/100g) ISO 787/5-1980	-
	Spec. Surface Area(m ² /g)	-
Loose Bulk Density (g/l)	1200	
Chemical Analysis	SiO ₂	71 %
	Al ₂ O ₃	15 %
	K ₂ O	6 %
	CaO	0,3 %
	Fe ₂ O ₃	2 %
	MgO	2 %
	TiO ₂	0,3 %
	Na ₂ O	0,1 %
	P ₂ O ₅	0,1 %
	LOI at 600°C	<2,00 %

Aspolit W 58 - 500

Particle Size
 Distribution
 Sieving

d98
 d90
 d50
 d30

500,0 μm
 450,0 μm
 350,0 μm
 300,0 μm



Technical information and data described herein are believed to be reliable, but should not be taken as a specification and cannot establish any liability!

REV 2/06-2018

Aspanger Bergbau und Mineralwerke GmbH & Co KG
 Neustift am Hartberg 25
 A-2870 Aspang
 Tel.: +43 2642 52355-0
 Fax.: +43 2642 52673
 E-Mail: office@aspanger.com
 Homepage: www.aspanger.com